

Technical sheet

Product description	A water-soluble, low-emission coloured epoxy material.		
Application	<ul style="list-style-type: none">• Material for use inside buildings as a finishing layer for vapour-permeable systems• Protection of concrete against dusting,• Can be applied for light and medium loads,• Material dedicated to warehouses, garages, production areas, etc.• Impregnation and strengthening of all types of mineral substrates.		
Properties	<ul style="list-style-type: none">• Very high adhesion,• Vapour-permeable material,• Good penetration of mineral substrates,• Matt finish,• Material available in a wide range of colours,• Low viscosity,• Possibility of application on vertical surfaces after priming with SICONOFLOOR AQUAPOX RC100,• Low VOC emissions,• Water-soluble,• High coverage,• Ease of application (long working life),• Short working breaks between successive layers (possibility of applying two layers in one day),• Versatility of applications,• Frost resistance,• Reduced tendency to crystallize.		
Physical properties of Siconofloor AQUAPOX RC100			
Character	Component A modified epoxy liquid		
	Component B amine hardener		
Density (according to PN EN ISO 1675)	Component A	1.05~1.2 g/cm ³	
	Component B	0.99~1.3 g/cm ³	
Working life	5 hours for a temperature of 20°C		
Theoretical consumption of the mixture	0.2-0.25 kg/m ² when applying with a velour roller on 1 layer of material for smooth surfaces, for rough surfaces the consumption increases		
Colour and smell	Component A white, odourless epoxy emulsion		
	Component B coloured and odourless		
Hygiene tests	Strongly depends on the intended use, substrate quality (absorptivity), application technique, application conditions, degree of roughness. Average consumption 0.2-0.25 kg/m ² . Two layers of resin are recommended for porous substrates.		
Practical consumption of the mixture	0.1~0.2 kg/m ² when applying with a velour roller on 1 layer of material		
Curing time	24h light loads at 25°C		
	Full load capacity		7 days
	Component A	2600-2900 mPa*s	
Viscosity (according to Brookfield DV-II). Test performed at 20 °C with a 04 spindle and 20 RPM rotational speed.	Component B		2200-2600 mPa*s
	Mechanical properties of SICONOFLOOR AQUAPOX RC100		
Content of non-volatile substances (according to PN-EN ISO 3251:2008)	80°C	97.91 ± 1 %	
	105°C	97.00 ± 1 %	
ShA hardness (after 7 days)	100°		
ShD hardness (ShD hardness after 7 days 80 ShD) (refers to thin resin applied with a roller on a concrete substrate)	10°	after 24h 75° ShD	
		after 48h 80° ShD	
	20°	after 24h 70° ShD	
		after 48h 80° ShD	
Application			
Application methods	Pre-mix component A and B, (mixing ratio 100A:360B), then mix the components until a homogeneous consistency is obtained, but not less than 3 minutes. The mixing ratio of Component A and Component B is shown on the packaging and must not be changed. Changing the proportions will result in a product with properties different from those declared by the Manufacturer. Mixing for too long may cause air entrainment and should therefore be avoided. To mix the resin, use a low speed electric stirrer (300 ~ 400 rpm) or other equipment designed for this. Application temperature +5-30°C (optimal +10-29°C).		
Finishing layer for floor or wall	Apply SICONOFLOOR AQUAPOX RC100 with a brush or roller according to the art of painting, make sure that a uniform, continuous coating is obtained, if necessary, apply a second layer after the first one is bound. Thick layers of material cannot be applied. Application is allowed only with a velour roller or a paint brush.		

Storage conditions for kit components	The SICONOFLOOR AQUAPOX RC100 resin is a material with a reduced tendency to undergo the crystallization process. It should be stored in a dry place at a temperature of 5~30°C. Component A and B in liquid state are water polluting agents and should not get into the sewage system, ground or water courses. After hardening, the resin is neutral for the environment.
Comments and recommendations	
Health and safety conditions	During all work with resins, use protective clothing, gloves and glasses. Adequate ventilation must be provided when working in confined or closed rooms, and during drying. When working, do not weld and do not come close to open fire sources. Use lighting lamps with appropriate safety measures. Detailed information on health, safety, as well as data on ecological, toxicological properties of the material, etc. are available in the Material Safety Data Sheet for SICONOFLOOR AQUAPOX RC100. Avoid contact with skin. Avoid breathing vapours from heated material. Do not allow individual components to come into contact with acids, strong oxidants, bases. All employees should be thoroughly trained in the handling of epoxy resins and hardeners with regard to the existing hazards. Allergy sufferers must not be commissioned to work with resins. If there is a risk of splashing the resin, use protective gloves and goggles. After each contact of the resin with the skin, wash with water with the addition of mild cleaning agents, do not use benzene, toluene or carbon tetrachloride! For hygiene reasons, you should not eat or drink in the workplace, and also not smoke there.
Concluding remarks	<p>The technical data provided is based on laboratory trials and tests. Practical measurement results may differ from the attached ones, due to circumstances over which Sicon Sp. z o.o. Sp.K. has no control. All information is given in good faith and takes into account the current state of knowledge and experience.</p> <p>The manufacturer informs that the colour of the finished floor may vary. This phenomenon does not indicate a defect of the floor or reduced technical parameters. Possible discolouration may appear because of the way in which work and drying take place. It is recommended to cover specific surfaces with batches of materials from one production batch. The product documentation provides general information that is appropriate under certain conditions.</p> <p>Prior to large-scale use of the product, it is recommended that the purchaser perform an application test under the specific environmental conditions of the construction site. The supplier has no influence on the types of applications, methods of application and conditions of implementation occurring on a construction site, therefore, these instructions cannot result in his responsibility for the final result of the application. Recommendations of Sicon's associates that deviate from the information contained in the technical sheet, are binding only if confirmed in writing.</p> <p>Date of issue: 02/2019</p> <p>All sheets for the Siconofloor AQUAPOX RC100 system issued so far shall expire on the day of the issuing of this sheet.</p>